

**RHEOFALT® LT-70****Technical Data Sheet**14<sup>th</sup> January 2015

**Synthetic paraffin. It contains an effective oxidation inhibitor**

**PRODUCT DATA**

<b>Properties</b>	<b>Standard</b>	<b>Unit</b>	<b>Specification</b>
Congealing point	DIN ISO 2207	°C	68 - 72
Penetration at 25 °C	DIN 51 579	0.1 mm	9 - 16
Oil content	DIN ISO 2908	%	max. 0,5
Viscosity at 100 °C	DIN 51 562 / T1	mm <sup>2</sup> /s	type. 5.9
Color, Saybolt	DIN 51 411	-	min. +28
Color	visual	-	white
Density at 70 °C	DIN 51 757	kg/m <sup>3</sup>	780
Dosage	2-4 m/m % on bitumen		

*All information given and recommendations made herein are based upon research and are believed to be accurate and complete. The information in this document refers only to the specified product. The information is not to be copied, used in evidence, released for publication or public distribution without written permission from Ventraco Chemie B.V.*