



RHEOFALT WKR-2

01-08-2014

PRODUCT DATA

Properties	Method	Specifications	
Concealing point	ASTM D 3104	102 – 108 °C	
Penetration at 25 °C	ASTM D 1321	0 – 4 *0.1mm	
Viscosity at 160 °C	ASTM D 3236	3200 - 4000 Mpa.s	
Shape		pallets	
Color	visible	yellow / brown	
Advised mixture with Bitumen 80-100		15-20%	

EFFECTS ON BITUMEN

%-addition		0	18	
Bitumen 80/100		100	82	
Concealing point *1		50 °C	78 °C	
Penetration *2	25 °C	76-80	26	
	40 °C	> 300	80	
Viscosity	140 °C	365 Mpa.s	1250 Mpa.s	
	160 °C	140 Mpa.s	450 Mpa.s	
	180 °C	70 Mpa.s	220 Mpa.s	

We reserve the right to change the specifications as a result of technical progress or for reasons related to production.
No guarantee or warranty is implied as to any particular applications of our products.